

Cold rolled steel suitable for cold forming according to 10130:1999

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1.0330 1.0347	DC01 DC03	Pickled Pickled	St12, CR4, FeP01, 1142 St13, CR3-CR2, FeP02, 1146

Hot rolled steel suitable for cold forming according to UNE EN 10111:1998

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1,0332	DD11	Mill finish/ Pickled	AP11, StW22, HR3, 1C, FeP11

Continuously hot-dip zinc coated steel suitable for cold forming according to UNE EN 10142:2001

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1,0226	DX51D	Galvanized	FeP02GZ/GZF, St01Z, A653CQ

Structural steels according to UNE EN 10025:2006

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1,0037 1,0044 1,0045 1,0577	S235JR S275JR S355JR S355J2	Mill finish/ pickled Mill finish Mill finish Mill finish	St37-2, Fe 360B, NC12120, E24-2, F111, A570 Gr36 St44-2, Fe430B, 43B, AE255-B Fe510B, E36-2, 50B, AE355B, F112, St52-3, A572 Gr50 St52-3N, 50D, AE355D, St510D

Structural steel with high yield strength suitable for cold forming according to UNE EN 10149-2:1996

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1,0976 1,0984 1,0982 1,8974	S355MC S500MC S420MC S700MC	Mill finish Mill finish Mill finish Mill finish	FeE355-TM, QStE360TM, E355D, 46F40, 2642-00 QStE500TM , 2662-00 FeE420-TM, QSt420TM, E445D, 50F45, 2652-00 QStE690TM, E690D, 75F70

Abrasion resistant steels

SYMBOLIC DESIGNATION	HARDNESS HB	FINISH	BRANDS
Antiwear steel HB400 Antiwear steel HB450 Antiwear steel HB500	370-430 425-475 450-540	Sand blasted+Painted Sand blasted+Painted Sand blasted+Painted	Dillidur400, Creusabro 400, Hardox 400, Roc 400 Dillidur450, Creusabro 450, Hardox 450, Roc 450 Dillidur500, Creusabro 500, Hardox 500, Roc 500

Structural steels with improved atmospheric corrosion resistance according to UNE EN 10155

NUMERICAL DESIGNATION	SYMBOLIC DESIGNATION	FINISH	DESIGNATIONS ACCORDING TO OTHER STANDARDS
1,8959	S355J0W	Mill finish	Corten

Steels for quenching and tempering according to UNE EN 10083-2

NUMERICAL DESIGNATION

1,1191
--

SYMBOLIC DESIGNATION

F114
F513-calibrated plate

FINISH

Mill finish
Mill finish

DESIGNATIONS ACCORDING TO OTHER STANDARDS

Ck45, XC45, C45, AISI 1045
C75W3, W1-0,8C, XC85, G4401SK5, AISI 1065

Steel for pressure purposes according to UNE EN 10028-2

NUMERICAL DESIGNATION

1.0425

SYMBOLIC DESIGNATION

P265 GH

FINISH

Sand blasted

DESIGNATIONS ACCORDING TO OTHER STANDARDS

Fe-410-1Kw, A42CP, A515-60

Structural steel used in ship construction according to ASTM 131

NUMERICAL DESIGNATION

F6501
--

SYMBOLIC DESIGNATION

NAVAL A
AH36

FINISH

Sand blasted
Sand blasted

DESIGNATIONS ACCORDING TO OTHER STANDARDS

A131/a131M-94, BV-A, GL-A, Grade A
BV-DH36, GL-DH36, LR-DH36